

ENSIGN SOIL

Short Radius Bend 30°

EF002

DESCRIPTION

The short radius bend is designed to offer a smooth transition of direction within a pipe system.

The short radius bend conforms to BS 12056-2 and can be used for soil, vent and rainwater systems.


RECOMMENDED USE

- Domestic use
- Wastewater
- Rainwater
- Runoff water
- Hot effluents

STANDARDS & APPROVALS

- Industry product standard: BS EN 877
- Range fire classification: A1

IDENTIFICATION LABEL



MATERIALS & COATINGS

- Cast Iron
- Internally and externally coated red-brown, anti-corrosive epoxy powder coating, average thickness 150 µm internally and 70µm externally

TECHNICAL FEATURES

- Hot water resistance: 24hr @ 95°C
- Thermal cycle resistance: 1500 cycles between 15°C and 93°C
- Chemical resistance for 2>ph>12
- Salt spray resistance internal coating: more than 350hrs.

ENVIRONMENTAL DATA

- Percentage of recycled content: 99%
- Recycling information: Cast Iron is 100% recyclable through the existing recycling industrial network.

Data source: Environmental Product Declaration S-P-02190



pam


building

ENSIGN SOIL

Short Radius

Bend 30°

EF002



DN	L	H	W	A	B	WEIGHT (KG)	PRODUCT CODE
50	76	97	58	45	69	0.5	191434
70	99	113	78	50	73	0.7	191439
100	132	136	110	60	81	1.3	191444
150	189	188	160	80	108	3.0	191456
200	243	229	210	95	124	7.0	155933
250	309	270	274	110	133	9.7	155948
300	367	322	326	130	159	15.5	155960
400	478	369	429	429	173	34.6	264752

This document is provided for information purposes, and our company reserves the right to modify the information contained herein at any time. Our company declines all responsibility of materials that do not comply with the rules prescribed in this document as well with the standards, the technical documents and the applicable professional standards. Any orders placed will be subject to our General Terms and Conditions of Sale, available on request. The drawings and/or images are the exclusive property of Pam Building and are confidential. They must not be reproduced or disclosed to any third party without written consent. They may only be used for the purpose for which they were issued and are returnable on request.